
PREPARATION AND PROPERTIES OF SINGLE CRYSTALS OF HYDROGEN BISCPHTHALOCYAN. (U) NORTH CAROLINA UNIV AT CHAPEL HILL DEPT OF CHEMISTRY B H SULLIVAN ET AL. 15 AUG 84 TR-23 N00014-76-C-0016 F/G 7/2 AD-8144 933 1/1 UNCLASSIFIED



MICROCOPY RESOLUTION TEST CHART NATIONAL BUREAU OF STANDARDS 1963-A

ŗ

SECURITY CLASSIFICATION OF THIS PAGE (187-11 Date)	Entered)	
REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. SOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
23		
. TITLE (and Subitite)		5. TYPE OF REPORT & PERIOD COVERED
Preparation and Properties of Single Cry- stals of Hydrogen Bis(Phthalocyaninato) Neodymium(III)		Technical Report, Interim
		6. PERFORMING ORG. REPORT HUYSER
7. AUTHOR(*) Brian W. Sullivan, Raymond N. Dominey, Jeffrey H. Helms, Michael Schwartz, Leonard W. ter Haar, and William E. Hatfield		NOO014-76-C-0816
3. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry 045A University of North Carolina Chapel Hill, North Carolina 27514		10. PROGRÀM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
ontrolling office name and address ffice of Naval Research epartment of the Navy		12. REPORT DATE August 15, 1984
rlington, Virginia 22217		13. NUMBER OF PAGES 8
IONITORING AGENCY NAME & ADDRESS(Il dillerent	from Controlling Office)	15. SECURITY CLASS. (of this report)

ISTRIBUTION STATEMENT (of this Report)

pproved for Public Release, Distribution Unlimited



Unclassified

15. DECLASSIFICATION/DOW:

DISTRIBUTION STATEMENT (of the abstract entered in Block 20, If different from Report)

This document has been approved for public release and sale; its distribution is unlimited.

13. SUPPLEMENTARY NOTES

Prepared for publication in Molecular Crystals and Liquid Crystals

13. KEY WORDS (Continue on reverse side if necessary and identify by block number)

phthalocyaninatoneodymium neodymium(III) phthalocyanine

semiconductor magnetic properties

23. ABSTRACT (Continue on reverse side if necessary and identify by block number)

Single crystals of hydrogen bis(phthalocyaninatoneodymium(III) have been synthesized by electrochemical means. The crystals are semiconductors and follow Curie-Weiss behavior.

08 28 J09

DD TORM 1473 LEDITION OF THOVES IS ODSOLETE

OFFICE OF NAVAL RESEARCH

Contract N00014-76-C-0816 Task No. NR 053-617 TECHNICAL REPORT NO. 23

PREPARATION AND PROPERTIES OF SINGLE CRYSTALS OF HYDROGEN BIS (PHTHALOCYANINATO) NEODYMIUM(III)

Ву

Brian W. Sullivan, Raymond N. Dominey, Jeffrey H. Helms, Michael Schwartz, Leonard W. ter Haar, and William E. Hatfield

Prepared for publication in Molecular Crystals and Liquid Crystals

Reproduction in whole or in part is permitted for any purpose of the United States Government.

This document has been approved for public release and sale; its distribution is unlimited.

PREPARATION AND PROPERTIES OF SINGLE CRYSTALS OF HYDROGEN BIS(PHTHALOCYANINATO) NEODYMIUM(III)

Brian W. Sullivan, Raymond N. Dominey, Jeffrey H. Helms, Michael Schwartz, Leonard W. ter Haar, and William E. Hatfield
Department of Chemistry, The University of North Carolina, Chapel Hill, North Carolina 27514

Abstract Single crystals of hydrogen bis(phthalo-cyaninato)neodymium(III) have been synthesized by electrochemical means. The crystals are semiconductors and follow Curie-Weiss behavior.

INTRODUCTION

Partially oxidized metallomacrocycles yield low-dimensional conducting materials. For example, NiPcI (Pc = phthalocyanine) crystallizes with the formation of stacked, planar NiPc units and exhibits metal-like conductivity parallel to the stacking direction. Lanthanide elements form sandwich-type compounds with phthalocyanine. Pressed pellet samples of hydrogen bis(phthalocyaninato)neodymium(III), [bis(Pc)Nd(III)], and bis(Pc)Nd(III)Iy (y = 1.3 and 1.8) exhibit semi-conductive behavior with room temperature conductivities of 4.5 x 10⁻³, 6.4 x 10⁻² and 0.8 x 10⁻¹ \(\text{cm}^{-1} \) cm⁻¹, respectively. It has been reported that single crystals of PcMPc (M = lanthanide(III) and Pc (32H16N8)) can be obtained via electrochemical oxidation of the corresponding hydrogen bis(phthalocyaninato)M(III). In this paper, we report the electrochemical synthesis, electrical conductivity, and magnetic behavior of single crystals of bis(Pc)Nd(III).

EXPERIMENTAL

The synthesis and purification of bis(Pc)Nd(III) was adopted from previously described methods. 5 The growth of single crystals was

achieved by electrochemical means similar to that reported for the preparation of PcNdPc .4 To 10 ml dimethylformamide and 0.1 ml hydrazine monohydrate was added 0.26 g bis(Pc)Nd(III). Upon filtration of the deep blue solution into an electrochemical cell fitted with a Pt wire (anode), graphite rod (auxillary electrode), and argon inlet and outlet tubes, a 0.150 V potential corresponding to an initial anodic current density equal to circa. 0.5 mA cm⁻² was applied. After 48 hours, dark blue PcNdPc crystals were collected at the Pt wire and were also filtered from solution.

Four probe contacts were used for these preliminary conductivity measurements. Gold wire (0.1 mm diameter) leads were connected at both ends of the crystals with silver paste. A DC current of approximately 10⁻⁵ A was used for the variable temperature data sets. Temperatures were measured with a silicon diode. Ohmic behavior was observed for all samples.

Magnetic susceptibility data between 77 and 300 K were collected under helium using a Faraday balance fitted with a Cahn 2000 electronic balance. Calibration was accomplished with Hg[Co(NCS)₄] and diamagnetic corrections, except for Nd(III), were made by using Pascal's constants. Temperatures were measured with a silicon diode.

RESULTS

Only the electrical conductivity along the long axis of each crystal, which presumably corresponds to the stacking direction of PcNdPc, was measured. The observed room temperature conductivities of three samples ranged from 0.008-0.04 Ω^{-1} cm⁻¹ and variable temperature resistivity data indicated semi-conductive behavior. When $\ln \rho$ was plotted versus temperature, the low temperature (78-210 K) data were approximately linear and could be fit to the thermally activated transport model $\sigma = \sigma_{\Omega} \exp(-\frac{\Lambda}{k} T)$

HYDROGEN BIS (PHTHALOCYANINATO) NEODYMIUM (III)

where J_0 is the infinite temperature conductivity, and $\Lambda(0.031 \text{ eV})$ per electron) is the energy of activation in this region. At temperatures greater than ~210 K, marked deviations from linearity occur. Most notably, between 210 and 260 K, a steep (~20 fold) rise in conductivity with increasing temperature was observed. Perhaps reminiscent of an exhaustive region of a semi-conductor, this peak was followed by a region (260-285°) in which conductivity significantly decreased with increasing temperature before the earlier temperature dependent behavior was resumed.

Magnetic susceptibility data for PcNdPc closely follows Curie-Weiss type behavior [X = C/(T-0)]. Using a non-linear least squares fitting routine, C and 0 were calculated to be 1.64 and -4.93 K respectively. The magnetic moment of 3.61 μ_B at 300 K is close to the value of 3.62 μ_B expected for a Nd(III) species. The values of μ_{eff} showed only a minor dependence on temperature; at 80 K μ_{eff} is 3.52 μ_B .

DISCUSSION

Utilizing the synthetic scheme described above, Moskalev et. al. 4 reported the isolation of crystalline PcNdPc $_{\rm OX}$. The reaction was assumed to involve the removal of an electron from the π -orbital of one phthalocyanine ring. In our hands, however, crystals of HPcNdPc were obtained instead. While exhibiting very similar infrared absorbances (874, 1053, 1108, 1213, 1351, and 1438 cm $^{-1}$) and lattice parameters (tetragonal; a=13.85 Å, c=6.62 Å) to those reported for the oxidized complex, the magnetic susceptibility measurements ($\mu_{\rm eff}=3.61$ $\mu_{\rm B}$) are consistent only with the presence of Nd(III); no further contribution from a Pc $_{\rm OX}$ species was observed.


Although single crystals of hydrogen bis(phthalocyaninato)
Nd(III) display increased conductivities relative to pressed
pellet samples, only semi-conductive behavior was observed.

However, partial oxidation of these crystals is expected to increase the electrical conductivity and perhaps make it metallic. Pressed pellet samples of bis(Pc)Nd(III)I exhibit an 18-fold increase in conductivity on going from y = 0 to y = 1.8. Likewise, samples (y = 0) exposed to oxygen display conductivities greater than those kept under hydrogen. The effect of partial oxidation should be even more pronounced in single crystals where full advantage of the one-dimensional stacks can be taken. In this light, it may be noted that NiPcI_{1.0} is metallic only in crystalline form. Reflective single crystals of iodinated bis(PC)Nd(III) have been obtained and are currently being studied.

ACKNOWLEDGEMENT This work was supported in part by the Office of Naval Research.

REFERENCES

- C.J. Schramm, R.P. Scaringe, D.R. Stojakovic, B.M. Hofimann, J.A. Ibers, T.J. Marks, J. Amer. Chem. Soc., 102, 6702 (1980).
- 2. K. Kasuga, M. Tsutsui, R.C. Petterson, K. Tatsumi, N. van Opdenbosch, G. Pepe, E.F. Meyer, Jr., J. Amer. Chem. Soc., 102, 4835 (1980).
- 3. L.W. ter Haar, W.E. Hatfield, M. Tsutsui, Molec. Cryst., 107, 181 (1983).
- 4. P.N. Moskalev, G.N. Shapkin, A.N. Darovskikh, Russ. J. Inorg. Chem., 24, 188 (1979).
- 5. I.S. Kirin, P.N. Moskalev, Y.U. Makashev, Russ. J. Inorg. Chem., 10, 1065 (1965).
- 6. M. Yamana, M. Tsutsui, J.S. Ham, <u>J. Chem. Phys.</u>, <u>76</u>, 2761 (1982).





	302011
Ву	
	1bution/
Avai	lability Codes
Dist	Avail and/or Special

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	No. Copies		No. Copies
Office of Naval Research		Naval Ocean Systems Center	
Attn: Code 413		Attn: Mr. Joe McCartney	
800 North Quincy Street		San Diego, California 92152	1
Arlington, Virginia 22217	2		
		Naval Weapons Center	
ONR Pasadena Detachment		Attn: Dr. A. B. Amster,	
Attn: Dr. R. J. Marcus		Chemistry Division	
1030 East Green Street		China Lake, California 93555	. 1
Pasadena, California 91106	1		
		Naval Civil Engineering Laboratory	
Commander, Naval Air Systems Command		Attn: Dr. R. W. Drisko	
Attn: Code 310C (H. Rosenwasser)		Port Hueneme, California 93401	1
Department of the Navy			
Washington, D.C. 20360	1	Dean William Tolles	
		Naval Postgraduate School	
Defense Technical Information Center	•	Monterey, California 93940	1
Building 5, Cameron Station			
Alexandria, Virginia 22314	12	Scientific Advisor	
		Commandant of the Marine Corps	
Dr. Fred Saalfeld		(Code RD-1)	
Chemistry Division, Code 6100		Washington, D.C. 20380	1
Naval Research Laboratory		-	
Washington, D.C. 20375	1	Naval Ship Research and Development	
		Center	
U.S. Army Research Office		Attn: Dr. G. Bosmajian, Applied	
Attn: CRD-AA-IP		Chemistry Division	
P. O. Box 12211		Annapolis, Maryland 21401	1
Research Triangle Park, N.C. 27709	1	•	
,		Mr. John Boyle	
Mr. Vincent Schaper		Materials Branch	
DTNSRDC Code 2803		Naval Ship Engineering Center	
Annapolis, Maryland 21402	1	Philadelphia, Pennsylvania 19112	1
- ·		• • • • • • • • • • • • • • • • • • • •	
Naval Ocean Systems Center		Mr. A. M. Anzalone	
Attn: Dr. S. Yamamotó		Administrative Librarian	
Marine Sciences Division		PLASTEC/ARRADCOM	
San Diego, California 91232	1	Bldg 3401	
-		Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST, 053

	No. Copies		No. Copies
Dr. M. F. Hawthorne Department of Chemistry University of California Los Angeles, California 90024	1	Dr. T. Marks Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. D. B. Brown Department of Chemistry University of Vermont Burlington, Vermont 05401	1	Dr. J. Zuckerman Department of Chemistry University of Oklahoma Norman, Oklahoma 73019	1
Dr. D. Venezky Chemistry Division Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Professor O. T. Beachley Department of Chemistry State University of New York Buffalo, New York 14214	1
Dr. John E. Jensen Hughes Research Laboratory 3011 Malibu Canyon Road Malibu, California 90265		Professor K. M. Nicholas Department of Chemistry Boston College Chestnut Hill, Massachusetts 02167	1
Dr. A. Cowley Department of Chemistry University of Texas Austin, Texas 78712	1	Professor R. Neilson Department of Chemistry Texas Christian University Fort Worth, Texas 76129 Professor M. Newcomb	1
Dr. W. Hatfield Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514	1	Texas A&M University Department of Chemistry College Station, Texas 77843 Professor Richard Eisenberg	1
Dr. M. H. Chisholm Department of Chemistry Indiana University Bloomington, Indiana 47401	1	Department of Chemistry University of Rochester Rochester, New York 14627	1
		Professor R. D. Archer University of Massachusetts Chemistry Department Amherst, Massachusetts 01003	